

## Technical information

	Fire behaviour tested in acc. with	EN ISO 9239-1 EN ISO 11925-2 EN 13501-1	≥ 8kW/m <sup>2</sup> Pass B <sub>f1-s1</sub>
	Slip resistance	EN 13893 DIN 51130 / BGR181 EN 13845 Annex C DIN 51097	≥ 0.30 / DS R10 ESb C
	Sound insulation	EN ISO 140-8	ca. 13 dB
	Flooring type	EN 13845	Safety flooring
	Thickness	EN ISO 24346	2 mm
	Wear layer thickness	EN ISO 24340	2 mm
	Roll dimensions	EN ISO 24341	2 m x 20 m = 40 m <sup>2</sup>
	Weight	EN ISO 23997	2.8 kg/m <sup>2</sup>
	Residual indentation	EN ISO 24343-1	≤ 0.10 mm
	Classification for use	EN ISO 10874	34, 43
	Flexibility	EN ISO 24344	Pass
	Dimensional Stability	EN ISO 23999	≤ 0.4 %
	Light fastness	EN ISO 105-BO2	≥ 6
	Castor chair abrasion	EN 425	Yes, type W
	Wear resistance	EN 13845 Annex D	≤ 10% / 50000 cycles
	Chemical resistance	EN ISO 26987	Good
	Under floor heating	EN 12524	Suitable
	Electrical behaviours	EN 1815	≤ 2 kV Antistatic
	VOC emissions	CDPH 1350 / Floorscore	Approved

**CE** 07 | Altro Limited, Works Road, Letchworth Garden City, Hertfordshire, SG8 1NW, UK | EN 13845 | DoP-No. 1010 | Reaction to fire Bfl-s1 | Slip Resistance: DS | EN 14041:2004/AC:2006 | 1029 Resilient floor covering to be used within a building



\*Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).



## Sustainability



## Installation and maintenance

Please refer to Altro installation and maintenance instructions. Failure to follow these instructions can affect product performance. Some materials are known to cause staining on vinyl floors. Typical examples include: asphalt and bitumen materials, cardboard / hardboard (wet), dyes from printed literature or packaging, rubber-backed carpets and rubber mats and rubber furniture rests and trolley wheels. Technical information on installation and staining can be found at [www.altro.com](http://www.altro.com)