



altro.com

**Designed for possibilities.
Made for people.**

Altro Transflor Motus





altro

Altro Transflor Motus



Umeda
MOT20008 (2.0 mm)
MOT25008 (2.5 mm)
WRM255 / A1M338 / LRV 41



Opole
MOT20006 (2.0 mm)
MOT25006 (2.5 mm)
WRM545 / A1M361 / LRV 25



Atocha
MOT20011 (2.0 mm)
MOT25011 (2.5 mm)
WRM544 / A1M27 / LRV 29



Sao Bento
MOT20012 (2.0 mm)
MOT25012 (2.5 mm)
WRM258 / A1M42 / LRV 13

Codes: WRM = weld rod, A1M = mastic, LRV = light reflectance value

Abkürzungen: WRM = Schweißschnüre, A1M = Altro mastic Dichtmasse, LRV = Lichtreflexionsgrad

Códigos: WRM = Cordón de soldadura, A1M = Mástique, LRV = Valor de reflectancia de la Luz



New Street
MOT20002 (2.0 mm)
MOT25002 (2.5 mm)
WRM261 / A1M85 / LRV 43



Piccadilly
MOT20001 (2.0 mm)
MOT25001 (2.5 mm)
WRM263 / A1M486 / LRV 33



Central
MOT20004 (2.0 mm)
MOT25004 (2.5 mm)
WRM531 / A1M84 / LRV 24



Union
MOT20005 (2.0 mm)
MOT25005 (2.5 mm)
WRM250 / A1M73 / LRV 8

Light reflectance values measured in accordance with BS 8493:2008.
Lichtreflexionsgrad (LRV) gemäß BS 8493:2008.
Los Valores de Reflectancia de la luz se miden de acuerdo con BS 8493:2008.



Paddington
MOT20009 (2.0 mm)
MOT25009 (2.5 mm)
WRM509 / A1M71 / LRV 21



Mandurah
MOT20003 (2.0 mm)
MOT25003 (2.5 mm)
WRM511 / A1M52 / LRV 21



Penn
MOT20010 (2.0 mm)
MOT25010 (2.5 mm)
WRM523 / A1M72 / LRV 10



Euston
MOT20007 (2.0 mm)
MOT25007 (2.5 mm)
WRM537 / A1M348 / LRV 9

Exact material match with samples cannot be guaranteed.
Eine exakte Übereinstimmung des Materials mit Mustern kann nicht garantiert werden.
Las muestras no pueden garantizar un color exacto.





















Typical applications / Typische Anwendungsbereiche / Zonas de instalación recomendadas

Commuter trains, intercity trains, metros, high-speed trains, airport transit shuttles, trams.

Pendler, Intercity, Hochgeschwindigkeits Zug oder Züge, U-Bahn, Transitbereich am Flughafen, Straßenbahnen.

Trenes de cercanías, Trenes interurbanos, Metro, Trenes de alta velocidad, Lanzaderas al aeropuerto, Tranvías.

Technical information / Technische Informationen / Información técnica

	Flooring type	Belagsart	Tipo de pavimento	EN 1817	Rubber floor Gummiböden Suelos de caucho
	Fire performance	Brandverhalten	Reacción al fuego	EN 45545-2 NFPA 130 ASTM E648 ASTM E662 BSS 7239	HL2 Pass Class 1 (≥ 0.50 W/cm ²) Ds (1.5) ≤ 100 Ds (4) ≤ 200 Fulfilled
	Slip resistance	Rutschhemmung/-sicherheit	Resistencia al deslizamiento	ASTM D2047 DIN 51130	≥ 0.6 R10
	Thickness	Gesamtdicke	Espesor total	EN ISO 24346	2.0 mm / 0.079" 2.5 mm / 0.098"
	Wear layer thickness	Nutzschichtdicke	Capa de uso	EN ISO 24340	2.0 mm / 0.079" 2.5 mm / 0.098"
	Classification for use	Nutzungsklasse	Áreas de uso	EN ISO 10874	34, 42 (2.0 mm) 34, 43 (2.5 mm)
	Flexibility	Flexibilität	Flexibilidad	EN ISO 24344	Pass / Bestanden / Conforme
	Dimensional Stability	Formstabilität	Estabilidad dimensional	EN ISO 23999	$\leq 0.4\%$
	Weight	Flächengewicht	Peso	EN ISO 23997	3.3 kg/m ² / 6.08 lb/sy (2.0 mm) 4.17 kg/m ² / 7.69 lb/sy (2.5 mm)
	Roll dimensions	Rollenformat	Dimensiones del rollo	EN ISO 24341	1.5 m x 15 m 4' 11" x 49' 2.5"
	Light fastness	Farbbeständigkeit/Lichtechtheit	Resistencia a la luz	EN ISO 105-BO2	≥ 6 Blue scale, ≥ 3 grey scale
	Wear resistance	Verschleißgruppe	Abrasión	ISO 4649 Procedure A (5 N)	≤ 250 mm ³
	Residual indentation	Resteindruck	Punzonamiento	EN ISO 24343-1	≤ 0.15 mm (2.0 mm) ≤ 0.20 mm (2.5 mm)
	Chemical resistance	Chemikalien-/Fleckenbeständigkeit	Resistencia a los productos químicos	EN ISO 26987	Good / Gut / Buena
	Castor chair abrasion	Stuhlrolleneignung	Huellas de sillas de ruedas	EN 425	Pass / Bestanden / Conforme
	Electrical behaviours	Elektrostatishes Verhalten	Caraterísticas eléctricas	EN 1815	≤ 2 kV, antistatic ≤ 2 kV, antistatisch ≤ 2 kV, antiestáticas
	Cigarette-burn resistance	Widerstandsfähigkeit gegen Zigarettenbrand	Resistencia a las quemaduras de cigarrillos	EN 1399	A ≥ 4 , B ≥ 3
	Shore A hardness	Shore A-Härte	Dureza (Shore A)	ISO 7619	≥ 75



Altro Limited a company certified by SGS to ISO 9001 and ISO 14001.

Installation and maintenance / Verlegung und Pflege / Instalación y mantenimiento

Please refer to Altro installation and maintenance instructions. Failure to follow these instructions can affect product performance. Technical information on installation and staining can be found at www.altro.com

Bitte beachten Sie die Altro Verlege- und Pflegeanleitungen. Erfolgt Verlegung und Pflege des Bodenbelags nicht gemäß Anleitung, kann sich dies auf die Eigenschaften auswirken. Technische Informationen zur Chemikalienbeständigkeit sowie zur Verlegung und Pflege finden Sie unter www.altro.com

Consulte las instrucciones de instalación y mantenimiento de Altro. El no respetar estas instrucciones podría afectar al rendimiento del producto. Para más información sobre mantenimiento o instalación de nuestros productos pincha aquí: www.altroscandess.com

 Altro, Designed for possibilities. Made for people. and Altro Transflor Motus are trademarks of Altro Limited.

United Kingdom

+44 (0) 1462 707 700

transportenquiries@altro.com

United States

+1 800 382 0333

transport@altrofloors.com

Canada

+1 800 565 4658

transport@altrofloors.com

Australia

+61 3 9764 5666

info@asf.com.au

China

+86 (0) 21 62363138

enquiries@altro.net.cn

Germany

+49 (0) 340 6500 0

anfrage@altro.de

Spain

+34 91 549 52 30

suelos@altroscandess.com